AECOM

APPENDIX B McPHILLIPS STREET PAVEMENT CORES

Pavement Coring Report

JOB No.: 60212147

DATE CORED: April 19, 2011

CLIENT: City of Winnipeg

CORED BY: Alarionov

PROJECT: Logan Avenue Reconstruction

GENERAL LOCATION: McPhillips Street between Notre Dame Avenue and Logan Avenue

CORE DIAMETER (mm): 150 mm

CORE No.	TEST LOCATION	Thickeness (mm)		
		Asphalt	Concrete	Total
CH11-01	Northbound Curb Lane, 8.0 m South of Winnipeg	70	185	255
CITTI-01	Ave., 1.5 m West of East Curb			
CH11-02	Northbound Centre Lane, 40.0 m North of McDermot	65	215	280
	Ave., 5.0 m West of East Curb			
CH11-03	Northbound Median Lane, 25.0 m North of William	45	205	250
	Ave., 8.0 m West of East Curb			
CH11-04	Northbound Curb Lane, 30.0 m North of train tracks	70	200	270
	North of Elgin Ave., 1.5 m West of East Curb			
CH11-05	Northbound Centre Lane, 28.0 m North of Pacific	70	110	180
	Ave., 5.0 m West of East Curb			
CH11-06	Northbound Median Lane, 8.0 m South of Logan Ave.,	140	0	140
	8.0 m West of East Curb			
CH11-07	Northbound Curb Lane, 40.0 m North of Logan Ave.,	30	180	210
	4.5 m West of East Curb			
CH11-08	Southbound Curb Lane, 20.0 m North of Logan Ave.,	50	185	235
	2.0 m East of West Curb			
CH11-09	Southbound Median Lane, 30.0 m South of Logan	55	190	245
	Ave., 4.0 m West of East Curb			
Notes:				

Notes:



MATERIALS LABORATORY

AECOM

99 Commerce Drive, Winnipeg, MB R3P 0Y7 Canada tel (204) 477-5381 fax (204) 284-2040



Photograph 1. - CH11-01



Photograph 2. – CH11-02




Photograph 3. - CH11-03




Photograph 4. - CH11-04



Photograph 5. - CH11-05



Photograph 6. - CH11-06



Photograph 7. - CH11-07



Photograph 8. - CH11-08



Photograph 9. - CH11-09