

## PART 1 - GENERAL

### 1.1 RELATED DOCUMENTS

- A. Drawings and general provisions of the Contract, including General and Supplementary Conditions and Division 01 Specification Sections, apply to this Section.

### 1.2 SUMMARY

- A. This Section includes one resinous flooring system, one with epoxy body.
  - 1. Application Method: Metal, power or hand troweled.

### 1.3 SUBMITTALS

- A. Product Data: For each type of product indicated. Include manufacturer's technical data, application instructions, and recommendations for each resinous flooring component required.
- B. Samples for Verification: For each resinous flooring system required, 5 inches (150 mm) square, applied to a rigid backing for color verification and texture. Separate from site Mock up sample required.
- C. Product Schedule: Use resinous flooring designations indicated in Part 2 and room designations indicated on Drawings in product schedule.
- D. Installer Certificates: Signed by manufacturer certifying that installers are certified and comply with specified requirements. To be presented to Contract Administrator at Pre-Award Meeting.
- E. Maintenance Data: For resinous flooring to include in maintenance manuals.

### 1.4 QUALITY ASSURANCE

- A. No request for substitution shall be considered that would change the generic type of floor system specified (i.e. epoxy mortar based system with decorative quartz topping). Equivalent materials of other manufacturers may be substituted only on approval of City of Winnipeg Contract Administrator in writing. Request will be subject to specification requirements described in this section.
- B. Installer Qualifications: General Contractor must engage an experienced installer (applicator) who is experienced in applying resinous flooring systems similar in material, design, and extent to those indicated for this Project, whose work has resulted in applications with a record of successful in-service performance, and who is acceptable to the resinous flooring manufacturer listed.
  - 1. Engage a resinous flooring installer who is currently certified in writing by resinous flooring manufacturer as qualified to apply the resinous flooring systems indicated.

2. Resinous Flooring installer must have a minimum 5-7 years of experience installing specified products, and shall have completed at least 10 projects of similar size and complexity.
- C. Source Limitations: Obtain primary resinous flooring materials, including primers, resins, hardening agents, grouting coats, and topcoats, through one source from a single manufacturer, with not less than ten years of successful experience in manufacturing and installing principal materials described in this section. Provide secondary materials, including patching and fill material, joint sealant, and repair materials, of type and from source recommended by manufacturer of primary materials.
- D. Manufacturer Field Technical Service Representatives: Resinous flooring manufacture shall retain the services of Field Technical Service Representatives who are trained specifically on installing the system to be used on the project.
1. Field Technical Services Representatives shall be employed by the system manufacture to assist in the quality assurance and quality control process of the installation and shall be available to perform field problem solving issues with the installer.
- E. Mockups: Apply site mockups to verify selections made under sample submittals and to demonstrate aesthetic effects and set quality standards for materials, installation methods and execution.
1. Apply full-thickness mockups on 60-inch- (1524-mm-) square floor area selected by Contract Administrator.
    - a. Include 48-inch (1200-mm) length of integral cove base.
  2. Approved mockups may become part of the completed Work if undisturbed at time of Substantial Completion.
- F. Pre-installation Conference:
1. General contractor shall arrange a meeting not less than thirty days prior to starting work.
  2. Attendance:
    - a. General Contractor
    - b. City of Winnipeg Contract Administrator and Senior Accommodations Planner.
    - c. Manufacturer/Installer's Representative.
- 1.5 DELIVERY, STORAGE, AND HANDLING
- A. Deliver materials in original packages and containers, with seals unbroken, bearing manufacturer's labels indicating brand name and directions for storage and mixing with other components.
  - B. Store materials to prevent deterioration from moisture, heat, cold, direct sunlight, or other detrimental effects. Store material per product data sheet.

- C. All materials used shall be factory pre-weighed and pre-packaged in single, easy to manage batches to eliminate on site mixing errors. No on site weighing or volumetric measurements allowed.

## 1.6 PROJECT CONDITIONS

- A. Environmental Limitations: Comply with resinous flooring manufacturer's written instructions for substrate temperature, ambient temperature, moisture, ventilation, and other conditions affecting resinous flooring application.
  - 1. Maintain material and substrate temperature between 65 and 85 deg F (18 and 30 deg C) during resinous flooring application and for not less than 24 hours after application.
- B. Lighting: Provide permanent lighting or, if permanent lighting is not in place, simulate permanent lighting conditions during resinous flooring application.
- C. Close spaces to traffic during resinous flooring application and for not less than 24 hours after application, unless manufacturer recommends a longer period.
- D. Concrete substrate shall be properly cure. A vapor barrier must be present for concrete subfloors on or below grade. Otherwise, an osmotic pressure resistant grout must be installed prior to the resinous flooring

## 1.7 WARRANTY

- A. Manufacturer shall furnish a single, written warranty covering both material and workmanship for a period of (1) full years from date of installation, or provide a joint and several warranty signed on a single document by material manufacturer and applicator jointly and severally warranting the materials and workmanship for a period of (1) full year from date of installation. A sample warranty letter must be included with bid package or bid may be considered non-compliant.

## PART 2 - PRODUCTS

### 2.1 RESINOUS FLOORING

- A. Available Products: Subject to compliance with requirements, products that may be incorporated into the Work include,
  - 1. Must comply with troweled mortar base with broadcast topping. Liquid rich, slurry type systems will not be accepted, and will result in a disqualification from bid.
- B. Acceptable Manufactures,
  - 1. Stonhard Basis of design.
- C. Products: Subject to compliance with requirements:
  - 1. Stonhard, Inc.; Stonshield HRI®.
- D. System Characteristics:

1. Color and Pattern: Glacier
  2. Wearing Surface: Medium Texture.
  3. Integral Cove Base: 6" high.
  4. Overall System Thickness: nominal 3/16"
- E. System Components: Manufacturer's standard components that are compatible with each other and as follows:
1. Primer:
    - a. Material Basis: Stonhard Standard Primer
    - b. Resin: Epoxy
    - c. Formulation Description: (2) two component, 100 percent solids.
    - d. Application Method: Squeegee and roller.
    - e. Number of Coats: (1) one.
  2. Mortar Base:
    - a. Material design basis: Stonshield HRI Base
    - b. Resin: Epoxy.
    - c. Formulation Description: (3) three component, 100 percent solids.
    - d. Application Method: Metal Trowel.
      - 1) Thickness of Coats: nominal 1/8" (inch).
      - 2) Number of Coats: (1) One.
    - e. Aggregates: Pigmented Blended aggregate.
    - f. Maintain 1% slope to existing drain.
    - g. Install berm at shower entrance between Washroom 203 and Shower 204; height to be 2" high tapered down to zero.
  3. Undercoat:
    - a. Material Basis: Stonshield undercoat.
    - b. Resin: Epoxy
    - c. Formulation Description: (2) two-component, 100% solids, UV Stable.
    - d. Type: Clear.
    - e. Finish: Gloss.
    - f. Number of Coats: (1) one.
  4. Broadcast Media:
    - a. Material Basis: Stonshield quartz aggregate
    - b. Type: pigmented.
    - c. Finish: standard.
    - d. Number of Coats: (1) one.
  5. Sealer:
    - a. Material Basis: Stonkote CE4.
    - b. Resin: Epoxy
    - c. Formulation Description: (2) two-component, 100% solids, UV Stable.
    - d. Type: Clear.
    - e. Finish: Gloss.
    - f. Number of Coats: (2) Two.
    - g. Texture level: Medium.

Note: Components listed above are the basis of design intent; all bids will be compared to this standard including resin chemistry, color, wearing surface, thickness, and installation procedures, including number of coats. General Contractor shall be required to comply with all the requirements of the Specifications and all of the components required by the Specifications, whether or not such products are specifically listed above.

- F. System Physical Properties: Provide resinous flooring system with the following minimum physical property requirements when tested according to test methods indicated:
1. Compressive Strength: 10,000 psi after 7 days per ASTM C579
  2. Tensile Strength: 2,000 psi per ASTM C307
  3. Flexural Strength: 4,300 psi per ASTM C580
  4. Flexural Modulus of Elasticity:  $2.0 \times 10^6$  psi per ASTM C580
  5. Hardness: 85 to 90 per ASTM D2240, Shore D
  6. Impact Resistance: > 160 in./lbs. per ASTM D2794
  7. Abrasion Resistance: 0.06 gm max. weight loss per ASTM D 4060, CS-17
  8. Flammability: Class 1 per ASTM E-648.
  9. Thermal Coefficient of Linear Expansion:  $1.3 \times 10^{-5}$  in./in. °F
  10. Water Absorption: 0.1% per ASTM C 413
  11. VOC Content per ASTM D2369:
    - a. Stonshield HRI Base – 40 g/l
    - b. Stonshield Undercoat – 34 g/l
    - c. Stonkote CE4 – 34 g/l
  12. Cure Rate @ 77°F/25°C: 12 hours foot traffic, 24 hours normal operations

## 2.2 ACCESSORY MATERIALS

- A. Patching, Leveling and Fill Material: Resinous product of or approved by resinous flooring manufacturer and recommended by manufacturer for application indicated.
- B. Joint Sealant: Type recommended or produced by resinous flooring manufacturer for type of service and joint condition indicated. Allowances should be included for Stonflex MP7 joint fill material.

## PART 3 - EXECUTION

### 3.1 PREPARATION

- A. General: Prepare and clean substrates according to resinous flooring manufacturer's written instructions for substrate indicated. Provide clean and dry substrate for resinous flooring application.
- B. Concrete Substrates: Provide sound concrete surfaces free of laitance, glaze, efflorescence, curing compounds, form-release agents, dust, dirt, grease, oil, and other contaminants incompatible with resinous flooring.
1. Mechanically prepare substrates as follows:
    - a. Shot-blast surfaces with an apparatus that abrades the concrete surface, contains the dispensed shot within the apparatus, and recirculates the shot by vacuum pickup, or Diamond Grind with dust free system.

2. Repair damaged and deteriorated concrete according to resinous flooring manufacturer's written recommendations.
3. Verify that concrete substrates meet the following requirements.
  - a. Perform in situ probe test, ASTM F 2170. Proceed with application only after substrates do not exceed a maximum potential equilibrium relative humidity of 85 percent.
  - b. Perform anhydrous calcium chloride test, ASTM F 1869. Proceed with application only after substrates have maximum moisture-vapor-emission rate of 6 lb of water/1000 sq. ft. of slab in 24 hours.
  - c. Perform additional moisture tests recommended by manufacturer. Proceed with application only after substrates pass testing.
- C. Use patching and fill material to fill holes and depressions in substrates according to manufacturer's written instructions.
- D. Treat control joints and other non-moving substrate cracks to prevent cracks from reflecting through resinous flooring according to manufacturer's written recommendations. Allowances should be included for Stonflex MP7 joint fill material, and CT5 concrete crack treatment.

### 3.2 APPLICATION

- A. General: Apply components of resinous flooring system according to manufacturer's written instructions to produce a uniform, monolithic wearing surface of thickness indicated.
  1. Coordinate application of components to provide optimum adhesion of resinous flooring system to substrate, and optimum intercoat adhesion.
  2. Cure resinous flooring components according to manufacturer's written instructions. Prevent contamination during application and curing processes.
  3. At substrate expansion and isolation joints, provide joint in resinous flooring to comply with resinous flooring manufacturer's written recommendations.
    - a. Apply joint sealant to comply with manufacturer's written recommendations.
- B. Integral Cove Base: Stonshield cove mortar, apply cove base mix to wall surfaces before applying flooring. Apply according to manufacturer's written instructions and details including those for taping, mixing, priming, troweling, sanding, of cove base. Round internal and external corners. Coves to be smooth to the touch, no nibs/aggregate protruding through seal coat.
  1. Integral Cove Base: 6" inches high; Color to match floor.
- C. Apply primer where required by resinous system, over prepared substrate at manufacturer's recommended spreading rate.
- D. Apply metal trowel single mortar coat in thickness indicated for flooring system into wet primer. Hand or power trowel and grout to fill voids. When cured, sand to remove trowel marks and roughness.
- E. Undercoat: Remove any surface irregularities by lightly abrading and vacuuming the floor surface. Mix and apply undercoat with strict adherence to manufacturer's installation procedures and coverage rates.

- F. Broadcast: Immediately broadcast quartz silica aggregate into the undercoat using manufacturer's specially designed spray caster. Strict adherence to manufacturer's installation procedures and coverage rates is imperative.
- G. Apply topcoat(s) in number of coats indicated for flooring system and at spreading rates recommended in writing by manufacturer.

### 3.3 TERMINATIONS

- A. Chase edges to “lock” the flooring system into the concrete substrate along lines of termination.
- B. Penetration Treatment: Lap and seal resinous system onto the perimeter of the penetrating item by bridging over compatible elastomer at the interface to compensate for possible movement.
- C. Trenches: Continue flooring system into trenches to maintain monolithic protection. Treat cold joints to assure bridging of potential cracks.
- D. Treat floor drains by chasing the flooring system to lock in place at point of termination.

### 3.4 JOINTS AND CRACKS

- A. Treat control joints to bridge potential cracks and to maintain monolithic protection.
- B. Treat cold joints and construction joints and to maintain monolithic protection on horizontal and vertical surfaces as well as horizontal and vertical interfaces.
- C. Vertical and horizontal contraction and expansion joints are treated by installing backer rod and compatible sealant after coating installation is completed. Provide sealant type recommended by manufacturer for traffic conditions and chemical exposures to be encountered.

### 3.5 FIELD QUALITY CONTROL

- A. Final Resinous flooring application must match approved site mock up samples.

### 3.6 CLEANING, PROTECTING, AND CURING

- A. Cure resinous flooring materials in compliance with manufacturer's directions, taking care to prevent contamination during stages of application and prior to completion of curing process. Close area of application for a minimum of 24 hours.
- B. Protect resinous flooring materials from damage and wear during construction operation. Where temporary covering is required for this purpose, comply with manufacturer's recommendations for protective materials and method of application. General Contractor is responsible for protection and cleaning of surfaces after final coats.
- C. Cleaning: Remove temporary covering and clean resinous flooring just prior to final inspection. Use cleaning materials and procedures recommended by resinous flooring manufacturer. General contractor is responsible for cleaning prior to inspection.

The City of Winnipeg  
Tender No. 280-2020  
WFPS Station 13 – Interior Building Renovations, 799 Lilac Street

Section 096723  
RESINOUS FLOORING

**END OF SECTION 096723**